

PolyKar[®] ELASTIK

Polyester putty, category : Putties

DESCRIPTION AND USAGE

PolyKar ELASTIK is elastic, middle dense, very well workable fast putty, suitable both as filling and upper putty for filling of middle and small disparities. It is intended for common surface including cast-iron, aluminum, zinc and glass fiber. It is without pits, very elastic, applicable to even out disparities on wood (harder kinds), concrete etc. The putty is very well applicable and has good sand ability.

ENVIRONMENT

The putty must not be used for filling places which are in direct contact with food and drinking water.

APPLICATION

Bonded surface must be without rust and old coatings. It is necessary to degrease the surface carefully, eventually to roughen with sanding paper:

- glass fiber – sanding paper P40
- steel, wood, cast-iron – sanding paper P60
- original coatings – sanding to bare metal with using of sanding paper P60

HARDENING

The putty is hardened with hardener (PE-initiator, dibenzoyl peroxide, red paste in tube) in weight ratio:

- 100 parts of putty : 2 parts of hardener – recommended ratio for temperature 20°C

POT LIFE

The putty is necessary to be used within 5 minutes after mixing with hardener at temperature 20°C and hardening ratio 100:2. Pot life can be extended at temperatures lower than 20°C (minimally 17°C) and shortened at higher temperatures. Modification of hardening ratio can partly eliminate temperature influence on pot life.

Hardening ratio:

- minimally 100 : 1 – pot life extended
- maximum 100 : 3 – pot life shortened

SANDING

The putty is sand able after 20 – 30 minutes at temperature 20°C and hardening ratio 100:2. Dry sanding starts with sanding paper P80 and finishes with sanding paper P180 – P240.

UPPER COATINGS

It is possible to use all common paint systems on the putty. The putty resists common baking temperatures 80 – 110°C. If it is necessary to use the putty on anticorrosive primer and bake the enamel after that, then we recommend use the baking primer, or more precisely two-component epoxy primer. We don't recommend using of air-drying synthetic coatings and baking after that.

TOOLS CLEANING

Dirty parts of tools for filling can be cleaned with thinner for polyester sealers B6000 or nitro thinner C6000. Only non-hardened putty can be cleaned.

SKLADOVÁNÍ A BALENÍ

It is necessary to ensure the temperature from +5°C to + 25°C and avoid direct solar radiation during storage and transport. Dash of the resin on the surface of putty is acceptable. We guarantee shelf life and quality of the product for 12 months.

Packaging:

- 0,2 kg, 0,5 kg, 1 kg, 2 kg, 5 kg, 15 kg – a can
- 3 kg – a can for batching plant

COLOUR

White

BKP GROUP, a. s.